



Certificate of Analysis

Standard Reference Material 339

17 Chromium-9 Nickel-0.2 Selenium Steel

| ANALYST | C | Mn | P | S | Si | Cu | Ni | Cr | V | Mo | Co | Se |
|---------------|-------------------|---------------------|-------------------------|-----------------------------|-----------------------------|-------------|------------------------------------|--|-------------|-------|---------|---------|
| | Direct combustion | Persulfate-Arsenite | Photometric | Combustion Iodate titration | Perchloric acid dehydration | Photometric | Weighed as nickel dimethylglyoxime | FeSO ₄ -KMnO ₄ titration | Photometric | | | |
| 1..... | 0.052 | a.0.732 | b.0.135 | c.0.013 | d.0.652 | e.0.201 | 8.87 | f.17.41 | g.0.058 | 0.247 | h.0.099 | i.0.248 |
| 2..... | { .050 | { .737 | b.130 | .014 | a.646 | l.197 | 8.92 | f.17.43 | | .24 | m.091 | n.250 |
| 3..... | .052 | k.732 | | .014 | .64 | o.195 | 8.88 | p.17.46 | | .252 | h.093 | i.243 |
| | { .048 | { .739 | a.133 | r.014 | .665 | s.198 | 8.93 | f.17.43 | t.063 | .247 | b.100 | i.246 |
| | { .051 | | | | | | | | | | | |
| 5..... | .056 | k.740 | { u.128 { v.011 { w.013 | { .125 { .011 { .013 | d.653 | w.198 | 8.87 | x.17.39 | y.061 | .248 | z.099 | i.247 |
| 6..... | .057 | a'.745 | q.121 | r.015 | a.665 | b'.204 | | 17.42 | o'.x.052 | .255 | | |
| Averages..... | 0.052 | 0.738 | 0.129 | 0.013 | 0.654 | 0.199 | 8.89 | 17.42 | 0.058 | 0.248 | 0.096 | 0.247 |

^a Chromium removed by precipitation with NaHCO₃.

^b Molybdenum-blue photometric method. See J. Res. NBS **26**, 405 (1941) RP1386.

^c 1-g sample burned in oxygen at 1425 °C and sulfur dioxide absorbed in starch-iodide solution. Iodine liberated from iodide by titration, during the combustion, with standard KIO₃ solution. Titer based on 93 percent of the theoretical factor.

^d Double dehydration with intervening filtration.

^e Diethylthiocarbamate photometric method. See J. Res. NBS **47**, 380 (1951) RP2265.

^f Persulfate oxidation, potentiometric titration with ferrous ammonium sulfate.

^g Nitric acid oxidation, potentiometric titration with ferrous ammonium sulfate.

^h Nitroso-R photometric method.

ⁱ Sulfuric Acid-Iodometric titration method. ASTM method E30-36.

^j Conductometric method.

^k Periodate photometric method.

^l 2,2' biquinoline photometric method.

^m Tetraphenylarsonium chloride-cobalt complex photometric method.

ⁿ Selenium hydrolyzed with SO₂, filtered and weighed.

^o Neocuproine photometric method.

^p Persulfate oxidation, titration with ferrous ammonium sulfate using diphenylamine sulfonate indicator.

^q Alkali-molybdate method.

^r Titrating solution standardized by the use of a standard steel.

^s Diethylthiocarbamate photometric method.

^t Vanadium oxidized with KBrO₃, potentiometric titration with ferrous ammonium sulfate.

^u Gravimetric method (weighed as Mg₂P₂O₇).

^v Gravimetric method (weighed as BaSO₄).

^w H₂S-electrolytic method.

^x Persulfate oxidation, potentiometric titration with FeSO₄-K₂Cr₂O₇.

^y Phosphotungstovanadate photometric method.

^z Ion-exchange—Nitroso-R photometric method.

^{a'} NaHCO₃-NaBiO₃ oxidation-NaAsO₂ titration.

^{b'} H₂S-CuS-CuO.

^{c'} Ether—FeSO₄-(NH₄)₂S₂O₈-KMnO₄.

List of Analysts

- 1. B. B. Bendigo and J. I. Shultz, Division of Analytical Chemistry, National Bureau of Standards.
- 2. M. J. Noll and A. L. Sloan, Carpenter Steel Co., Reading, Pa.
- 3. W. M. Gross and R. E. Hanson, General Dynamics-Convair, San Diego, Calif.
- 4. R. W. Bley, Inland Steel Co., East Chicago, Ind.
- 5. M. D. Cooper, A. H. Jones, R. E. Kohn, W. R. Lee, R. B. Loranger, and H. E. Vergosen, General Motors Corp. Research Laboratories, Warren, Mich.
- 6. A. C. Hale and D. R. Burrier, Copperweld Steel Co., Warren, Ohio.

The steel for the preparation of this standard was furnished by the Carpenter Steel Co.

Washington, D. C.
 July 21, 1965

W. Wayne Meinke, Chief,
 Office of Standard Reference Materials.